

TECHNICAL DATA SHEET

2K POLYURETHANE ENAMEL TOPCOATFOR EXTERIOR

Product Code: Part A 2421, 222X, PUXX Part B 42T9

Product Description

A two component, specially formulated premium quality acrylic polyurethane designed to provide maximum beauty and protection of exterior and interior wood surfaces. It's pigmented, gloss-matt finish is extremely durable.

Intended Used

For exterior and interior woodwork

• Outdoor and indoor furniture, all wood substrates.

Features

- Excellent flow on level surface
- Good scratch resistance and polished
- Excellent over-coat ability
- Chemical and water resistance
- Excellent durable and gloss retention

Product Information

Finish Pigmented Gloss - Matt

Color Opaque **Specific gravity** 1.25 – 1.35

Solid Approx. 60 - 65% by mass

Application Detail

Mixing Stir before use, until homogeneous

Substrate Wood

Method Conventional spray, airless spray

Thinning Thin with POLYURETHANE THINNER (1194) **Mixing Ratio** For Spray; 2421/2250 : 42T9 : 1194 = 4:1:4

Drying time Touch dry: 20 minutes

Hard dry: 6 hours

Recoat time: 2 - 3 hours

Cleaning Tools and equipment should be cleaned by POLYURETHANE

THINNER (1194) after use.

Addition Data

Coverage 8 m² per litre at 125 micron wet film build.

Pot life 2-5 hr.
Shelf life 1 year



TECHNICAL DATA SHEET

Surface preparation

<u>General</u>: The entire surface area should be clean, dry, sound and free from dirt, grease, oils, waxes, dust and any other surface contaminants that may adversely affect the performance of this coating material.

<u>New Wood Surfaces</u>: Thoroughly sand the surface area smooth, progressing in sand paper usage starting with rough grit sandpaper to medium grit sandpaper to fine grit sandpaper. Always sand in the same direction of the wood grain. Finial screen or sand the surface with 120 or 150 grit sanding screen, or 180 to 220 grit sandpaper. After sanding and screening, vacuum the surface to remove all sanding dust. Final wipe the surface with a tack rag or a cloth dampened with mineral spirits, and allow to dry. All cracks, gouges, dents and other surface imperfections should be properly repaired with wood putty that does not contain any wax. Allow all repairs to dry thoroughly, then sand smooth. Wood surfaces that are to be stained should be allowed to dry thoroughly after staining.

<u>Previously Stained & Varnish Wood Surfaces</u>: Previously stained and varnished wood surface that are in good condition should be thoroughly cleaned as stated above. The entire surface should be lightly sanded to remove imperfections and to dull glossy finishes. Remove any loose, scaling, cracked or chipping areas of existing varnish by hand scraping, sanding, and wire brushing or by use or power tool cleaning methods, such as electric sanders, etc. Previously stained and varnished wood surfaces that are in poor condition should be completely stripped to the bare wood substrate and finish as new wood. Repair/replace all damaged, deteriorated, and surface imperfections with the proper patching compounds or building materials and allow to dry thoroughly.

Primer: 2K POLYURETHANE PRIMER Part A 2387: Part B 2151

Packaging

Available in 1 Gallon/Set, 5 Gallon/Set

Storage

Should be taken to protect vessels and partial containers from moisture. Partial containers must be purged with a dry, inert gas, such as dry air, nitrogen or argon before closure, otherwise premature polymerization by atmospheric moisture will occur.

Cautions

The following is a summary of the precautions to be taken when handling this product. Please refer to the SDS for further details.

The toxicological properties of this material have not been fully determined. Products of this type can be expected to be eye and skin irritant and have the potential to cause sensitization or other allergic responses. Appropriate precautions should be taken to avoid eye and skin contact and to avoid.